
Technical Datasheet

LL 22401
(with UV)

1) Applications:

- High stiffness blown films, blending
- Lamination/ film

2) Typical data:

PROPERTIES	TEST METHOD	UNIT	TYPICAL VALUE*
Melt Flow Rate (190 °C, 2.16kg)	ISO 1133	gr/10min	0.8-1.1
Density	ISO 1183	gr/ml	0.920-0.923
Dart Impact	ASTM D 1709-03	gr	65
Tensile Strength at Yield	ASTM D882-10	MPa	18-21
Tensile Strength at Break	ASTM D882-10	MPa	54-36
Elongation at break	ASTM D882-10	%	780-990
Elmendorf TearStrength	ASTM D1922-09	g/25 μ m	35-325

Address: No. 3, 12th Floor, A Block, Babak Plaza Building, Babak Ave, Baku, Azerbaijan

Tel: +994 124880752 | Email: mr.info@mrchemicalaz.com | www.mrchemicalaz.com

