
Technical Datasheet

LL 22402
(with UV)

1) Applications:

- For use in lean and rich blend blown film application such as overwrap, counter bags, shrink film and boil in the bag applications
- Artificial grass

2) Typical data:

PROPERTIES	TEST METHOD	UNIT	TYPICAL VALUE*
Melt Flow Rate (190 °C, 2.16kg)	ISO 1133	g/10min	1.8-2.1
Density	ISO 1183	g/ml	0.920-0.923
Tensile Strength at Yield	ASTM D882-10	MPa	18-21
Tensile Strength at Break	ASTM D882-10	MPa	54-36
Elongation at break	ASTM D882-10	%	780-990
Elmendorf TearStrength	ASTM D1922-09	g/25 µm	35-325

Address: No. 3, 12th Floor, A Block, Babak Plaza Building, Babak Ave, Baku, Azerbaijan

Tel: +994 124880752 | Email: mr.info@mrchemicalaz.com | www.mrchemicalaz.com

