

Technical Datasheet

GPPS1240

1) Product Description:

GPPS1240 is a molecular weight crystal polystyrene for extrusion and injection moulding application with good mechanical properties.

2) Applications:

- ✓ Special extrusion
- ✓ Impact dilution
- ✓ Special injection molding

3) Typical data:

PROPERTY	TEST METHOD	UNIT	TYPICAL VALUE*
Melt Flow Rate (200 °C, 5kg)	ASTM D-1238	g/10min	2.5
Styrene Residual Monomer	CLG LABPSG004 (ATOFINA TEST METHOD)	PPM	<500
Vicat softening point (50 °C/hr 1kg)	ASTM D-1525	°C	96
Tensile Stress at Break	ASTM D-638	MPA	53
Elongation at Break	ASTM D-638	%	3
Tensile Modulus	ASTM D-638	MPA	4300

*All above mentioned data are typical values and not to be construed as real specifications. Density and shrinkage of this grade are approximately around 1.04 kg/lit & (0.4-0.7)% (ASTM D-955) respectively. All tests are carried out at 23°C, unless otherwise stated. If the injection molding products quality is affected by moisture, granules of GPPS could be dried at 70°C for 2-4 hours.

Address: No. 3, 12th Floor, A Block, Babak Plaza Building, Babak Ave, Baku, Azerbaijan

Tel: +994 124880752 | Email: mr.info@mrchemicalaz.com | www.mrchemicalaz.com