
Technical Datasheet

S5831

1) Applications:

- ✓ Rigid Films, Bottles, Fittings and Injection Molded Parts

2) Typical data:

PARAMETER	TEST METHOD	TYPICAL VALUE
K-Value	1628-2	57-59
Viscosity number (ml/g)	1628-2	79-86
Bulk density (g/l)	60	540-600
Grain size (% >63 μm)	4610	95-100
Grain size (% >250 μm)	4610	0-1
Porosity (%wt)	4608	14-20
Volatiles Matter (%wt)	1269	0.3>
Flowability (s/150g)	6186	25 \geq
Residual VCM (ppm)	6401	1 \geq
Dark Resin (Con./250g)	Vinnolit F5	20 \geq
Fish eyes(Counts/25cm ²)	Vinnolit H1	5 \geq

Address: No. 3, 12th Floor, A Block, Babak Plaza Building, Babak Ave, Baku, Azerbaijan

Tel: +994 124880752 | Email: mr.info@mrchemicalaz.com | www.mrchemicalaz.com