

---

## Technical Datasheet

### S6031

#### 1) Applications:

- ✓ Rigid and Semi-Rigid Profiles and Sheets

#### 2) Typical data:

PARAMETER	TEST METHOD	TYPICAL VALUE
K-Value	1628-2	59-61
Viscosity number (ml/g)	1628-2	84-92
Bulk density (g/l)	60	520-580
Grain size (% >63 µm)	4610	95-100
Grain size (% >250 µm)	4610	0-1
Porosity (%wt)	4608	16-22
Volatiles Matter (%wt)	1269	0.3>
Flowability (s/150g)	6186	25≥
Residual VCM (ppm)	6401	1≥
Dark Resin (Con./250g)	Vinnolit F5	20≥
(Fish eyes(Counts/25cm <sup>2</sup> ))	Vinnolit H1	5≥

---

Address: No. 3, 12th Floor, A Block, Babak Plaza Building, Babak Ave, Baku, Azerbaijan

Tel: +994 124880752 | Email: [mr.info@mrchemicalaz.com](mailto:mr.info@mrchemicalaz.com) | [www.mrchemicalaz.com](http://www.mrchemicalaz.com)