
Technical Datasheet

S6542

1) Applications:

- ✓ Semi-Rigid and Plasticized Profiles, Films and Flexible Articles

2) Typical data:

PARAMETER	TEST METHOD	TYPICAL VALUE
K-Value	1628-2	64-66
Viscosity number (ml/g)	1628-2	101-109
Bulk density (g/l)	60	460-520
Grain size (>63 μm)	4610	95-100
Grain size (>250 μm)	4610	0-1
Porosity (%wt)	4608	24-30
Volatiles Matter (%wt)	1269	0.3>
Flowability (s/150g)	6186	35 \geq
Residual VCM (ppm)	6401	1 \geq
Dark Resin (Con./250g)	Vinnolit F5	20 \geq
(Fish eyes(Counts/25cm ²))	Vinnolit H1	2 \geq

Address: No. 3, 12th Floor, A Block, Babak Plaza Building, Babak Ave, Baku, Azerbaijan

Tel: +994 124880752 | Email: mr.info@mrchemicalaz.com | www.mrchemicalaz.com