

Technical Datasheet

S7242

1) Applications:

- ✓ Plasticized Films and Profiles, Injection Molded Parts, Medical Tubes and Medical Gloves

2) Typical data:

PARAMETER	TEST METHOD	TYPICAL VALUE
K-Value	1628-2	71-73
Viscosity number (ml/g)	1628-2	127-137
Bulk density (g/l)	60	430-490
Grain size (>63 μm)	4610	95-100
Grain size (>250 μm)	4610	0-1
Porosity (%wt)	4608	30-35
Volatiles Matter (%wt)	1269	0.3>
Flowability (s150g)	6186	35≥
Residual VCM (ppm)	6401	1≥
Dark Resin (Con./250g)	Vinnolit F5	10≥
Fish eyes(Counts/25cm ²)	Vinnolit H1	2≥