
Technical Datasheet

S8040

1) Applications:

- ✓ Plasticized Films and Profiles, Sealing, Blood bags and Medical Tubes

2) Typical data:

PARAMETER	TEST METHOD	TYPICAL VALUE
K-Value	1628-2	79-81
Viscosity number (ml/g)	1628-2	163-175
Bulk density (g/l)	60	420-480
Grain size (% >63 μm)	4610	95-100
Grain size (% >250 μm)	4610	0-1
Porosity (%wt)	4608	30-35
Volatiles Matter (%wt)	1269	0.3>
Flowability (s150g)	6186	35 \geq
Residual VCM (ppm)	6401	1 \geq
Dark Resin (Con./250g)	Vinnolit F5	10 \geq
Fish eyes(Counts/25cm ²)	Vinnolit H1	2 \geq